

Product Data Sheet 2146

Nylon Cure Wrap, 2146 high tenacity					Made in Germany
Material:	Warp / Weft:	PA 6.6 / PA 6.6			
Yarn count:	Warp / Weft:	235 dtex / 110 dtex			
Weave:	Plain weave				
Melting point:	255 – 260 °C				
Technical Data	Unit	Nominal	Min.	Max.	Test Method
Warp density:	Picks / cm	39	37,5	40,5	DIN EN 1049-2
Weft density:	2 Picks / cm	17.5	16	19	DIN EN 1049-2
Breaking strength:	N / 50 mm	2900	2750	---	DIN EN ISO 13934-1
Elongation at 75% breaking strength:	%	19	15	23	DIN EN ISO 13934-1
Thickness:	mm	0,29	0,27	0,31	DIN EN ISO 5084
Weight:	g/m ²	137	127	147	DIN EN 12127
Making-up:	Rolled on cardboard core, inner-Ø 40 mm				
Length:	max.			1500 m	
Width:	20 – 290 mm	Standard: 40, 60, 70, 80, 100, 120, 150, 275 mm			
Tape width:	< 60 mm	60 - 80 mm		> 80 mm	
Width tolerance:	± 1 mm	± 1,5 mm		± 2 mm	